

Glasgow Tel: +44 (0) 141 620 1666 I Inverness Tel: +44 (0) 1463 238 673

<u>sales@williamjohnston.co.uk</u> I <u>www.williamjohnston.co.uk</u>

Black Neoprene Reinforced Sheeting to BS2752 C60 WJ196CT

PROPERTIES	TEST METHOD	VALUES
		METRIC UNITS
SPECIFIC GRAVITY	BS 903: PART A1	1.40
HARDNESS	BS 903: PART A26	60 ± 5 IRHD
TENSILE STRENGTH (KG/CM2)	BS 903: PART A2	130
ELONGATION AT BREAK (MIN)	BS 903: PART A2	350%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	BS 903: PART A6	25%
TEAR RESISTANCE (ANGULAR) MIN	BS 903: PART A3	35 Kg/cm
RESISTANCE TO ACCELERATED AGEING- 168HRS AT 70°C	BS 903: PART A19	
HARDNESS (Pts)	BS 903: PART A26	+ 7 (MAX)
TENSILE STRENGTH (%)	BS 903: PART A2	-12 (MAX)
ELONGATION AT BREAK (%)	BS 903: PART A2	-20 (MAX)
VOLUME SWELL: AT 40°C FOR 24 HRS/IN	BS 903: PART A16	
FUEL B		+ 70% (MAX)
RESISTANCE TO LOW TEMPERATURE AT - 40°C	BS 903: PART A13	MEETS REQUIREMENTS
ADHESION TO AND CORROSION OF METALS	BS 903: PART A 37	MEETS REQUIREMENTS
POLYMER CONTENT (NEOPRENE)		100%
Al	DDITIONAL INFORMATION -	
CHEMICAL RESISTANCE		
OZONE	BS 903: PART A 43	GOOD
DILUTE ACIDS AND BASES	BS 903: PART A16	GOOD
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED
MINERAL OILS - PARAFINNIC & NAPHTHANIC HC		GOOD
MINERAL OILS - AROMATIC HC		FAIR
ANIMAL/VEGETABLE OIL		GOOD
SOLVENTS		FAIR
TEMPERATURE RANGE		-30° TO + 120° C
COLOUR	BLACK	
FABRIC	1PLY 150GSM Nylon fabric reinforcement	

VOLUME SWELL DATA		
RESISTANCE TO LIQUIDS	BS ISO 1817, 24 <u></u> h at (40±1) °C	-0
VOLUME CHANGE (%) AFTER IMMERSION IN LIQUID B	BS ISO 1817, 24 ⁰ h at (40±1) °C -2	+70
RESISTANCE TO ACCELERATED AGEING	PART A19, AIR-OVEN METHOD A, (168±2) h, (70±1) °C	-0
CHANGE IN HARDNESS DEGREES (IRHD)	PART A26, METHOD N, MEASUREMENTS BEFORE AND AFTER AGEING ON THE SAME 2 PLIES EACH 2.00MM THICK	+7
MAXIMUM CHANGE IN TENSILE STRENGTH (% OF ORIGINAL VALUE)	PART A2, TYPE 1 OR TYPE 2 DUMBBELLS	-12
MAXIMUM CHANGE IN ELONGATION AT BREAK (% OF ORIGINAL VALUE)	PART A2, TYPE 1 OR TYPE 2 DUMBBELLS	-20

Disclaimer
Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.