



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Black Neoprene Flame Retardant Sheet 60° shore WJ187

Characteristics		Values
Specific Gravity		1.20
Hardness (° Shore A)		60 ± 5
Tensile Strength, (Kgf/cm ²), min		80
Elongation At Break, (%), min		250
Maximum compression set after 24h at 70°C, (%)		25
Flame resistance (according to ISO240)	Flame persistence (after removing the burner)	Max 45s
	The flame mustn't reappear after an air draughtiness application	Max 15
Antistatic characteristic (according to BS 490) Surface electrical resistance (Ω), max		3 x 10 ⁸
Temperature Range		-30° to +100°C
Compression Set (70°C for 22 hours), (%)		25
Polymer Content		Blend

Disclaimer

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.