



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Black Neoprene / SBR Rubber 70° shore WJ106

| PROPERTIES | TEST METHOD | VALUES FPS UNITS | TEST METHOD | VALUES METRIC UNITS |
|--|---------------|------------------|--------------------|---------------------|
| SPECIFIC GRAVITY | DIN 53508 | 1.45 ± 0.05 | ASTM D297 | 1.45 ± 0.05 |
| HARDNESS | DIN 53505 | 70 ± 5 SH A | ASTM D2240 | 70 ± 5 SH A |
| TENSILE STRENGTH (MIN) | DIN 53504 | 569 PSI | ASTM D412 | 40 KG/CM2 |
| ELONGATION AT BREAK (MIN) | DIN 53504 | 200% | ASTM D412 | 200% |
| COMPRESSION SET (70 °C/24 HRS/25% SET) (MAX) | DIN ISO 815-1 | 40% | ASTM D395 METHOD B | 40% |
| TEAR RESISTANCE (ANGULAR) MIN | DIN 53515 | 100 LBS/INCH | ASTM D624 | 18 KG/CM |
| CHANGE IN PROPERTIES | | | | |
| HEAT AGEING (72 HRS. AT 70 °C) | | | ASTM D573 | |
| --- HARDNESS (PTS) | | + 5 (MAX) | | + 5 (MAX) |
| --- TENSILE STRENGTH (%) | | + 10 / - 25 | | + 10 / - 25 |
| --- ELONGATION AT BREAK (%) | | + 10 / - 25 | | + 10 / - 25 |
| VOLUME SWELL : AT 70° C FOR 72 HRS/IN | | | ASTM D 471 | |
| IRM OIL NO.1 | | + 33% | | + 33% |
| IRM OIL NO.2 | | + 47% | | + 47% |
| IRM OIL NO.3 | | + 90% | | + 90% |
| POLYMER CONTENT (NEOPRENE) | | 10% | | 10% |
| CHEMICAL RESISTANCE | | | | |
| --- OZONE | | FAIR | ASTM D 1149 | FAIR |
| --- DILUTE ACIDS AND BASES | | FAIR | | FAIR |
| --- CONCENTRATED ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- OILS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- SOLVENTS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| TEMPERATURE RANGE | | -30 ° TO +90° C | | -30 ° TO +90° C |

| PROPERTIES | TEST METHOD | VALUES FPS UNITS | TEST METHOD | VALUES METRIC UNITS |
|------------|-------------|------------------|-------------|---------------------|
| COLOUR | | | BLACK | |

Disclaimer

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.