



sales@williamjohnston.co.uk

Glasgow Tel: +44 (0) 141 620 1666 I Inverness Tel: +44 (0) 1463 238 673 www.williamjohnston.co.uk

ECTFE Clear Teflon

Physical	Typical Value Unit	Test Method
Specific Gravity	1.68	ASTM D792
Water Absorption	< 0.10%	ASTM D570

Mechanical **Typical Value Unit Test Method Taber Abrasion Resistance** 5.00 mg **ASTM D1894** (1000 cycles, 500g, CS-17 wheel)

Film **Typical Value Unit Test Method** Thickness tested 50 µm Secant Modulus ASTMD882 MD 1550 MPa

1550 MPa

Film **Typical Value Unit Test Method** ASTM D882 Tensile strength MD: Break 53.0 MPa TD: Break 53.0 MPa

Tensile elongation ASTM D882

MD: Break 280% TD: Break 280%

Thermal Typical Value Unit Test Method Brittleness temperature -76°C ASTM D746A Melting temperature 242°C DMA Specific Heat (23°C) 962 J/kg/°C **ASTM D3418** Thermal conductivity (40°C) 0.15 W/m/K ASTM C177

TD

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.



Revision date: 5th February 2021





