



Product information

REV202111

Stuffing-Box-Packing Type 2070

Description

TEADIT style 2070 is diagonally braided from a proprietary yarn which consists of a core of Aramid fibers totally encased by gPTFE (PTFE with incorporated graphite), lubricated with silicone oil.

Properties

The unique, patented TEADIT EGK® yarn gives this packing exceptional properties. Every single yarn owns the most desirable characteristics: high mechanical strength from the Aramid core and the superior chemical resistance, self lubrication, low coefficient of friction and excellent heat dissipation from the external PTFE/graphite jacket. Chloride content < 20 ppm

Application areas

Style 2070 is an ideal packing for applications requiring highest chemical resistance and mechanical strength. It is recommended for rotating and reciprocating pumps, valves, mixers, agitators, etc., in the chemical, pharmaceutical and many other industries. TEADIT style 2070 is particularly suited for the demanding applications in refiners, digestors and similar equipment in the pulp and paper industry.

Application media

The superior extrusion resistance of style 2070 - four times higher than conventional gPTFE packings - makes it ideal for applications with chemically aggressive fluids at high shaft speeds and pressures. It can also be used in connection with water, sewage, steam, inert and aggressive gases, solvents, mineral oils and greases, abrasive media and many more.

Not suitable for

Molten alkali metals and fluorine compounds at high temperatures and pressures, oxygen.

Benefits

Because this exclusive packing - manufactured only by TEADIT - can be used in most applications by most industries, it can lower stock volumes considerably. No other packing combines so many advantages:
the strength of Aramid - without its abrasiveness and limited chemical resistance- and the suppleness, chemical resistance, low coefficient of friction and heat dissipation of PTFE/graphite - but without its extrusion problems.



Temperature:

	- temp	+ temp
(°C)	100	280

Pressure:

	rotating:	reciprocating:	static:
(bar)	35	250	250

pH: 0-14 density: (g/cm³) 1,6 v: (m/s) 25

Disclaimer

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences TEADIT® has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. TEADIT® does not undertake any liability of any kind whatsoever. Please note: the color of the actual product might vary from the above image on this data-sheet.