



# WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673  
[sales@williamjohnston.co.uk](mailto:sales@williamjohnston.co.uk) | [www.williamjohnston.co.uk](http://www.williamjohnston.co.uk)

## Black High Temperature FKM A Rubber 75° shore WJ14975FKM23

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	2.00 ± 0.05	ASTM D297	2.00 ± 0.05
HARDNESS	DIN 53505	75 ± 5 SH A	ASTM D2240	75 ± 5 SH A
TENSILE STRENGTH (KG/CM2)	DIN 53504	855 PSI	ASTM D412	50 KG/CM2
ELONGATION AT BREAK ( MIN )	DIN 53504	200%	ASTM D412	200%
COMPRESSION SET (150°C/24 HRS/25% SET) (MAX)	DIN 53517	45%	ASTM D395 METHOD B	45%
POLYMER CONTENT (%)				100
CHANGE IN PROPERTIES				
HEAT AGEING ( 48 HRS. AT 150 °C )			ASTM D573	
--- HARDNESS (PTS)		+ 5 (MAX)		+ 5 (MAX)
--- TENSILE STRENGTH (%)		+ 15		+ 15
--- ELONGATION AT BREAK (%)		+25 / -25		+25 / -25
VOLUME SWELL : AT 150°C FOR 24 HRS/IN			ASTM D 471	
ASTM OIL NO.1		-8%		-8%
ASTM OIL NO.2		-1%		-1%
ASTM OIL NO.3		+6%		+6%
CHEMICAL RESISTANCE				
--- OZONE		EXCELLENT	ASTM D 1149	EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		VERY GOOD		VERY GOOD
--- SOLVENTS		VERY GOOD		VERY GOOD
TEMPERATURE RANGE		-20° TO + 275° C		-20° TO + 275° C
COLOUR		BLACK		

### Disclaimer

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.

